

## PRECIPITATION HARDENING STAINLESS STEEL BAR

### TYPICAL APPLICATIONS

15/5 PH is very suitable for intricate parts requiring machining and welding and/or where distortion in conventional heat treatment is a problem. It is employed where high strength and good corrosion resistance are required. This alloy finds extensive use in aircraft and missile construction ranging from parts for instrumentation to landing gear components. 15/5 PH is also employed for valve parts, fittings, fasteners, shafts and gears and chemical process equipment and nuclear reactor components.

### PRODUCT DESCRIPTION

15/5 PH VAR is a martensitic, precipitation hardening stainless steel containing 4% copper. It possesses all the advantages of 17/4 PH, including single low-temperature thermal treatment. It also offers excellent transverse notch toughness and ductility and very good uniformity of properties. The mechanical properties in larger sections and forgability are superior to that of 17/4 PH. 15/5 PH VAR is produced by the consumable electrode, vacuum arc remelted route which enhances ductility and toughness and gives an essentially ferrite-free microstructure. This alloy has a typical density of 7.8 kg/dm<sup>3</sup> and magnetic permeability of 95.

### STOCK RANGE

**Round Bar (VAR) : 1/8" to 11" Diameter (3.18 to 279.4mm) Type 1**  
**Round Bar (ESR) : 1/2" to 7" Diameter (12.7 to 177.8mm) Type 2**

### CHEMICAL COMPOSITION (WEIGHT %)

	C	Mn	P	S	Si	Cr	Ni	Mo	Cu
Min						14.00	3.50		2.50
Max	0.07	1.00	0.030	0.015	1.00	15.50	5.50	0.50	4.50

### MECHANICAL PROPERTIES (MINIMA)

Condition	Tensile Strength (MPa)	0.2% Proof Stress (MPa)	Elongation on 4D G.L. (%)	Hardness (HB)
H900	1,310	1,172	10	388 / 444
H925	1,172	1,069	10	375 / 429
H1025	1,069	1,000	12	331 / 401
H1075	1,000	862	13	311 / 375
H1100	965	793	14	302 / 363
H1150	931	724	16	277 / 352

### TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

### Thames Stockholders

Unit 5W Woodall Road, Redburn Industrial Estate, Ponders End, Enfield EN3 4LQ

Tel: 020 8805 3282

Fax: 020 8804 8164

Email: sales@thamesstock.com

Website: www.thamesstock.com

*All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Thames Stockholders 2007*

### RELATED SPECIFICATIONS

ASTM SA-564 Type XM - 12  
UNS S15500

### CUT TO SIZE SAWN BLANKS

Cut to length in house to tolerances - Nil + 1.0mm

### MACHINABILITY / FORMABILITY

The forming characteristics are good.  
Average cutting speed – annealed, 80ft/min with a machinability rates of 50% of B-1112 rated at 100%. H1150, 125ft/min. Similar to 17/4 PH.

### CORROSION RESISTANCE

Superior to straight chromium grades like 410, approaching corrosion resistance of the chromium nickel grades. In many corrosive media it is equal to such grades as 302 (and even 304). Corrosion resisting properties will be affected by surface finish and aging heat treatment. Heat treatment increases the resistance to stress corrosion cracking.

### WELDABILITY

Excellent. Readily weldable by all commercial processes.

### PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Table AMS 2241. For further assistance please contact our Sales Dept / Laboratory.