

ALUMINIUM PLATE

TYPICAL APPLICATIONS

Aerospace Components
 Defence Components
 High Technology Applications

PRODUCT DESCRIPTION

A medium strength rolled plate, solution heat-treated, artificially aged and stress relieved arriving at the 'T651' condition. Officially, the scope of the specification covers only thicknesses between 6 and 25mm. Of these, only 12 to 25mm thick are ultrasonically tested. However, ultrasonically tested metal up to at least 127mm thick is commonly made to chemical composition only, although mechanical properties are usually achieved as well.

General Engineering Equivalent - 6082T651
 General Engineering Euronorm - EN 573 / 754
 Old BS - HP30TF (BS1470) Controlled Stretched
 AECMA Euronorm - BE EN 4202

STOCK RANGE

1/4" to 5" Thick
(6.35 to 127mm)

CUT TO SIZE SAWN BLANKS

Cut To Length and Width +/- 1.6mm

MACHINABILITY

Very Good.

CORROSION RESISTANCE

Resistance to Atmospheric Attack

Good

SURFACE TREATMENT

Anodising

Protective - Good
 Bright - Fair
 Hard - Good / Very Good
 Colour - Good

Plating

Special pre-treatment necessary to achieve successful results

Vitreous Enamelling

As Plating.

WELDABILITY

Brazing & Soldering - Good
 Oxygen - Fair
 Inert Gas - Very Good
 Resistance, Spot, Beam - Very Good

PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Section 14 of BS 4L100 – Tables 29 (F1, 2, 5, 7 & 8). For further assistance please contact our Sales Dept / Laboratory.

CHEMICAL COMPOSITION (WEIGHT %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Pb	Sn
Min	REM	0.7			0.4	0.5						
Max	REM	1.3	0.5	0.1	1.0	1.2	0.25	0.1	0.2	0.2	0.05	0.05

MECHANICAL PROPERTIES (MINIMA)

Size Range (mm)	Tensile Strength (MPa)	0.2% Proof Stress (MPa)	Elongation on 5.65 √ S ₀ (%)	Elongation on 50mm (%)
Up to 25mm	295	240	8	8

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Thames Stockholders

Unit 5W Woodall Road, Redburn Industrial Estate, Ponders End, Enfield EN3 4LQ

Tel: 020 8805 3282

Fax: 020 8804 8164

Email: sales@thamesstock.com

Website: www.thamesstock.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Thames Stockholders 2007