

ACRYLIC (PMMA)

ENGINEERING PLASTIC

PRODUCT DESCRIPTION

Acrylic (also known as Polymethyl-Methacrylate or PMMA) is an amorphous thermoplastic. The material offers a high strength to weight ratio, is optically transparent and unaffected by water. Often used as an alternative to glass, it should not be considered for structural applications due to the thermoplastic's poor impact resistance. Trade names for Acrylics include Acrylite®, Lucite® and Plexiglass®. Whilst acrylics are not recommended for use with chlorinated or aromatic hydrocarbons, ester or ketones, the material is unaffected by aqueous solutions of most detergents, acids, alkalis and laboratory chemicals.



KEY FEATURES

- UV resistant, low water absorption
- Good insulation properties
- Good stiffness and abrasion resistance
- Clear / colourable - clarity is excellent

AVAILABILITY

Sheet, rod and tube

APPLICATIONS

- Liquid chemical pumps, water tank liners
- Master cylinders
- Dashboard lighting
- Hard contact lenses, helmet visors

MECHANICAL PROPERTIES

Tensile Strength	(psi)	8,000 - 11,000
Tensile Modulus	(psi)	350,000 - 500,000
Tensile Elongation at break	(%)	2
Flexural Strength	(psi)	12,000 - 17,000
Flexural Modulus	(psi)	350,000 - 500,000
Compressive Strength	(psi)	11,000 - 19,000
Compressive Modulus	(psi)	-
Hardness	Rockwell	M80 - M100
IZOD Notched Impact	(ft-lb/in)	0.3

THERMAL PROPERTIES

Coefficient of Thermal Expansion	($\times 10^{-5}$ in./in./°F)	5 - 9
Flammability Rating	UL94	-
Heat Deflection Temperature @264	(psi)	150-210 / 65-100
Melting Temp	(°F / °C)	265-285 / 130-140
Max Operating Temp	(°F / °C)	150-200 / 65-93



Thames Stockholders

Unit 5W, Woodall Road, Redburn Industrial Estate
Ponders End, Enfield, Middlesex EN3 4LQ

t +44 (0)20 8805 3282
f +44 (0)20 8804 8164

w www.thamesstock.com
e sales@thamesstock.com



1930

www.thamesstock.com

sales@thamesstock.com

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.

© Thames Stockholders 2018